Amendments to the Specification:

Please replace the paragraph beginning on line 9 of page 10 with the following amended paragraph:

It is preferable that the compound having at least two polymerizable unsaturated groups and at ~~lest~~ least one aryl group in the molecule has the property such that the polymer obtained by curing this compound alone has a refractive index of 1.55 or greater, since the refractive index of the hard coat layer can be easily brought to a value of 1.53 or greater.

Please replace item (5) on page 4, lines 22 to 23 with the following amended item (5):

(5) A hard coat film according to any one of (1) to (4), wherein the substrate is a polyarbonate film or ~~polyethylenetelephthalate~~ a polyethyleneterephthalate film; and